

ETAP® BrownTop Kraft Liner Technical Data Sheet

(Guaranteed Values)

	Basis Weight	Bursting Strength	SCT, CD	Moisture	Cobb60
	[g/m ²]	[kPa]	[kN/m]	%	[g/m ²]
Standard	T-410	T-807	T-826	T-412	T-441
Tolerance	± 3 %	± 5 %	± 5 %	± 1.50 %	Average
	150	500	3.00	7	29/33
	200	630	3.80	7	29/33

Issue Date Jan 2023

BASIC INFORMATION

FSC® certified.

Made from 2 ply, top ply is 100% softwood Kraft fibers, Base ply is sorted Recycled fibers.

High compression strength

Reel diameters: 125 up to 140 cm

Standard Reel core size: 10 cm